

LENZI EGISTO by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599
- Fax + 39 (0) 574.946048/ 0574.22115
e-mail: lab.resp@lenzie.it – <http://www.lenzie.it>
Codice Fiscale /P.IVA 06270040485

Fabric Certificate:ADMIRAL

Certificate Issued:

Identification		Construction	
Reference name:	ADMIRAL	weight:(± 5%)	216 field gr/sqm (ISO 3801)
Usable width cm.:	150 (± 2%)	weight:(± 5%)	325 grs./lin mt. (ISO 3801)
		Comp.:	100%AR

Weaving			Warp	Weft
Finishing		End count	Yarns:	

Brands:

Performance

		Warp	Weft	Test Methods
Abrasion resistance: (nu Martindale)	60.000			ISO 12947 (9 kPa)
Tear strength: (Newton , singler tear)		>54	>64	EN ISO 13937-2
Pilling: (nu Martindale)	4			ISO 12947
Tensile Strength (Newton) Extension (Percentage)		>1300 55%	>1235 37%	BS EN ISO 13934-1(200mm100mm)

Handling instruction:

End-Use Suitability:

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto by FF laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto by FF reserve the rights to change paramethers with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto by FF can not be responsible for a fabric used when its thecnical caracteristic are not suitable for its end use.