

LENZI EGISTO by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599
- Fax + 39 (0) 574.946048/ 0574.22115
e-mail: lab.resp@lenzie.it – <http://www.lenzie.it>
Codice Fiscale /P.IVA 06270040485

Fabric Certificate: AIR FRESH STRONG PA

Certificate Issued: 2017-02-02

Identification		Construction	
Reference name:	AIE FRESH STRONG PA	weight:(± 5%)	270 field gr/sqm (ISO 3801)
Usable width cm.:	153 (± 2%)	weight:(± 5%)	413 grs./lin mt. (ISO 3801)
		Comp.:	68%PA 32%PL

Weaving			Warp	Weft
Finishing		End count	Yarns:	

Brands:

Performance				
		Warp	Weft	Test Methods
Abrasion resistance: (nu Martindale)	>20000			ISO 13520 (12 kPa)
Tear strength: (Newton , singler tear)		>176	>123	EN ISO 13937-2
Pilling: (nu Martindale)	4/5			ISO 13520
Tensile Strength (Newton) Extension (Percentage)		>1690 42%	>860 39%	BS EN ISO 13934-1(100mm100mm)

Handling instruction:

End-Use Suitability:

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto by FF laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto by FF reserve the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto by FF can not be responsible for a fabric used when its technical characteristics are not suitable for its end use.