

LENZI EGISTO by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599
 - Fax + 39 (0) 574.946048/ 0574.22115
 e-mail: lab.resp@lenzie.it – <http://www.lenzie.it>
 Codice Fiscale /P.IVA 06270040485

Fabric Certificate:AKRONOS

Document Issued: 19/04/2010

Identification		Construction	
Reference name:	AKRONOS	weight:(± 5%)	335 field gr/sqm (ISO 3801)
Usable width cm.:	145 (± 2%)	weight:(± 5%)	485 grs./lin mt. (ISO 3801)
		Comp.:	94%PL 6%LY

Weaving			Warp	Weft
Finishing		End count	Yarns:	

Brands: LYCRA®

Performance				
		Warp	Weft	Test Methods
Abrasion resistance: DRY: (nu Martindale)	>51.200			ISO 13520
WET:	>51.200			
Tear strength: (Newton , singler tear)		>170	>106	EN ISO 13937-2
Pilling: (nu Martindale)	4/5			ISO 13520
Tensile Strength (Newton)		>1471	>408	BS EN ISO 13934-1(200mm100mm)
Extension (Percentage)		31%	67%	
Seam slippage: (N): Seam:		>200	128	UNI EN 13936/1
Unseamed:		>200	>200	

Handling instruction:

End-Use Suitability:

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto Spa reserve the rights to change paramethers with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto spa can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.



LENZITECNOLINE®
 technical and research fabrics