

# LENZI EGISTO S.p.a.

## Industria Tessile

Capitale Sociale Euro 1.040.000,00 Int.Vers.

Sede Legale ed Uffici: Via G. Di Vittorio,39 – I – 59021 VAIANO Tel. +39 (0) 574.946030 - Fax + 39 (0) 574.946048

e-mail: [lab.resp@lenzie.it](mailto:lab.resp@lenzie.it) – http: www.lenzie.it

Codice Fiscale 039090380480 - P.IVA 002874809

### Fabric Certificate: BURT SINGOLO



Certificate Issued: 11/01/2010

Identification		Construction	
Reference name:	BURT SINGOLO	weight:(± 2%)	245 field gr/sqm (ISO 3801)
Usable width cm.:	145 (± 2%)	weight:(± 2%)	360 grs./lin mt. (ISO 3801)
		Comp.:	100%PA

Weaving			Warp	Weft
Finishing		End count	Yarns:	

Brands: CORDURA®

		Performance			
		Warp	Weft	Test Methods	
Abrasion resistance: DRY:	>100.000			UNI EN 13520 (12 Kpa)	
(nu Martindale) WET:	>100.000				
Tear strength:		74	74	EN ISO 13937-2	
(Newton , singler tear)					
Pilling: DRY:	4			UNI EN 13520	
(nu Martindale) WET:	4/5				
Hydrostatic Head (mbar)				ISO 14120 A	
Surface water repellent:				ISO 4920	
(spray test)					
Tensile Strength (Newton)		2071	1300	BS EN ISO 13934-1(200mm100mm/min)	
Extension (Percentage)		45%	36%		
Seam slippage (N) Seam:		>200	>200	EN ISO 13936/1	
Unseamed:		>200	>200		
Colour fastness Light				ISO 105 B-02	
Colour Dry fastness				ISO 105 D-01	
Colour Wet fastness				ISO 105 C-06	
Colour fastness Dry rubbing				ISO 105 X-12	
Colour fastness Wet rubbing					
Colour fastness perspiration				ISO 105 E-04	

Handling instruction:

End-Use Suitability:

**Note: Test reports carried out on single fabric. The results of the chosen bonding change the fabric-performances.**

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto Spa reserve the rights to change paramethers with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto spa can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.