

Fabric Certificate: CHAMOIX

Certificate Issued:

Identification		Construction	
Reference name:	CHAMOIX	weight:(± 5%)	140 field gr/sqm (ISO 3801)
Usable width cm.:	154 (± 2%)	weight:(± 5%)	216 grs./lin mt. (ISO 3801)
		Comp.:	100% PL

Performance

		Warp	Weft	Test Methods
Abrasion resistance: (nu Martindale)	> 20000			ISO 12947 (9 kPa)
Tear strength: (Newton , singler tear)		>8	>4	EN ISO 13937-2
Pilling: (nu Martindale)	4			ISO 12947
Tensile Strength (Newton) Extension (Percentage)		>227 30%	>138 32%	BS EN ISO 13934-1(200mm100mm)

Handling instruction:

End-Use Suitability:

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto by FF laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto by FF reserve the rights to change paramethers with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto by FF can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.

FF S.r.l.

Registred Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy

Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048

e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it

VAT Number: 06270040485