

# LENZI EGISTO by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599  
- Fax + 39 (0) 574.946048/ 0574.22115  
e-mail: [lab.resp@lenzie.it](mailto:lab.resp@lenzie.it) – <http://www.lenzie.it>  
Codice Fiscale /P.IVA 06270040485

## Fabric Certificate: CINQUECENTO NC4 CAMO WR FR

Certificate Issued: 12/11/2015

Identification		Construction	
Reference name:	CINQUECENTO NC4 CAMO WR FR	weight:(± 5%)	338 field gr/sqm (ISO 3801)
Usable width cm.:	150 (± 2%)	weight:(± 5%)	507 grs./lin mt. (ISO 3801)
		Comp.:	100%PA

Weaving			Warp	Weft
Finishing		End count	Yarns:	
Brands:				

Performance				
		Warp	Weft	Test Methods
<b>Abrasion resistance:</b> (nu Martindale)	>50.000			ISO 12947 (9 kPa)
<b>Tear strength:</b> (Newton , singler tear)		85	77	EN ISO 13937-2
<b>Pilling:</b> (nu Martindale)	4/5			ISO 12947
<b>Surface water repellent:</b> (spray test)	5			ISO 4920
<b>Tensile Strength</b> (Newton) <b>Extension</b> (Percentage)		1882 39%	1150 28%	BS EN ISO 13934-1(100mm100mm)
<b>Colour fastness Dry rubbing</b>	4/5			ISO 105 X-12
<b>Colour fastness Wet rubbing</b>	4/5			

### Handling instructions:



### End-Use Suitability:

### Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto by FF laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto by FF reserve the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto by FF can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.