

## Fabric Certificate: DYNAFELT 350 CT

Identification		Construction	
Reference name:	DYNAFELT 350 CT	weight:(± 10%)	350 field gr/sqm (ISO 3801)
Usable width cm.:	160 (± 2%)	Weight:(± 10%)	560 grs./lin mt. (ISO 3801)
Thickness :	2 mm (UNI 9073/2)	Comp.:	100% STAPLE FIBER

Weaving			Warp	Weft
Finishing	End count		Yarns:	
<b>DYNEEMA ST60/2 ( deriving from dyneema SK 75 fiber )</b>				

Performance				
		Warp	Weft	Test Methods
<b>Tear strength:</b> (Newton , singler tear)		>1333	>1045	UNI EN ISO 9073/4
<b>Tensile Strength</b> (Newton) <b>Extension</b> (Percentage)		>1153 >60%	>2013 >40%	UNI EN ISO 29073-3/93
<b>Resistance to cutting (circular saw blade)</b>	LEVEL 3			UNI EN 388

### Handling instruction & end-use suitability:



### Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. can not be responsible for a fabric used when its technical characteristics are not suitable for its end use.

#### FF S.r.l.

Registered Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy

Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048

e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it

VAT Number: 06270040485