

LENZI EGISTO® by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599
 - Fax + 39 (0) 574.946048/ 0574.22115
 e-mail: lab.resp@lenzie.it – <http://www.lenzie.it>
 Codice Fiscale /P.IVA 06270040485

Fabric Certificate:GRIZZLY STRONG TINTO

Document Issued: 01/09/2010

Identification		Construction	
Reference name:	GRIZZLY STRONG TINTO 2010	weight:(± 5%)	355 field gr/sqm (ISO 3801)
Usable width cm.:	155 (± 2%)	weight:(± 5%)	550 grs./lin mt. (ISO 3801)
		Comp.:	90%PA 10%LY

Weaving			Warp	Weft
Finishing		End count	Yarns:	

Brands: CORDURA®,LYCRA®

Performance				
		Warp	Weft	Test Methods
Abrasion resistance: (nu Martindale)	>50.000			ISO 12947 (9 kPa)
Tear strength: (Newton , singler tear)		>151	>203	EN ISO 13937-2
Pilling: (nu Martindale)	4/5			ISO 12947
Tensile Strength (Newton)		>2309	>1623	BS EN ISO 13934-1(200mm100mm)
Extension (Percentage)		56%	97%	
Seam slippage: (N) Seam:		125	143	UNI EN 13936-1 (3 mm)
Unseamed:		>200	>200	

Handling instruction:

End-Use Suitability:

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto Spa reserve the rights to change paramethers with no previous notice.We recommend that any fabric has to be carefully evaluated on the basis of final employ.Lenzi Egisto spa can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.



LENZITECNOLINE®
 technical and research fabrics