

## Fabric Certificate: HEXA FLAT STRETCH

Identification		Construction	
Reference name:	HEXA FLAT STRETCH	weight:(± 5%)	235 field gr/sqm (ISO 3801)
Usable width cm.:	127 (± 2%)	weight:(± 5%)	298 grs./lin mt. (ISO 3801)
		Comp.:	95%PA 5%LY

### Performance

		Warp	Weft	Test Methods
<b>Tear strength:</b> (Newton , singler tear)		>80	>54	UNI EN ISO 13937-2
<b>Tensile Strength:</b> (Newton) <b>Extension :</b> (Percentage)		>883 130%	>697 51%	UNI EN ISO 13934-1
<b>Abrasion resistance:</b> (nu Martindale)	dry: >51.200 wet:>51.200			UNI EN 13520 (12 kPa)
<b>Pilling:</b> (nu Martindale, after 51.200 revs)	severe			UNI EN 13520 (12kpa)

#### Note:

Please note that above mentioned data are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. cannot be responsible for a fabric used when its technical features are not suitable for its end use.

#### FF S.r.l.

Registred Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy  
 Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048  
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it  
 VAT Number: 06270040485