

## Fabric Certificate: HEXA STRETCH 17768

Identification		Construction	
Reference name:	HEXA STRETCH 17768	weight:(± 5%)	415 field gr/sqm (ISO 3801)
Usable width cm.:	126 (± 2%)	weight:(± 5%)	523 grs./lin mt. (ISO 3801)
		Comp.:	54%PA 40%PL 6%EA

### Performance

		Warp	Weft	Test Methods
<b>Tear strength:</b> (Newton , singler tear)		>80	>54	UNI EN ISO 13937-2
<b>Tensile Strength:</b> (Newton) <b>Extension :</b> (Percentage)		>883 130%	>697 44%	UNI EN ISO 13934-1
<b>Abrasion resistance:</b> (nu Martindale)	dry: >51.200 wet:>51.200			UNI EN 13520 (12 kPa)
<b>Pilling:</b> (nu Martindale, after 51.200 revs)	severe			UNI EN 13520 (12kpa)
<b>Repeated flexing test</b> ("bally" flexometer")		>150.000	>150.000	UNI 4818

#### Note:

Please note that above mentioned data are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. cannot be responsible for a fabric used when its technical features are not suitable for its end use.

#### FF S.r.l.

Registred Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy

Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048

e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it

VAT Number: 06270040485