

LENZI EGISTO S.p.a.

Industria Tessile

Capitale Sociale Euro 1.040.000,00 Int.Vers.

Sede Legale ed Uffici: Via G. Di Vittorio,39 – I – 59021 VAIANO Tel. +39 (0) 574.946030 - Fax + 39 (0) 574.946048

e-mail: lab.resp@lenzie.it – http: www.lenzie.it

Codice Fiscale 039090380480 - P.IVA 00287480974

Fabric Certificate: ICARO REFLEX 1PU

Certificate Issued:

Identification		Construction	
Reference name:	ICARO REFLEX 1PU	weight:(± 2%)	350 field gr/sqm (ISO 3801)
Usable width cm.:	147 (± 2%)	weight:(± 2%)	515 grs./lin mt. (ISO 3801)
		Comp.:	67% PA 30% PL 3% GL

Weaving			Warp	Weft
Finishing		End count	Yarns:	

Brands:

Performance				
		Warp	Weft	Test Methods
Abrasion resistance: (nu Martindale)	>50.000			ISO 12947 (9 kPa)
Tear strength: (Newton , singler tear)		>304	>233	EN ISO 13937-2
Tensile Strength (Newton) Extension (Percentage)		>2284 40%	>1627 46%	BS EN ISO 13934-1(100mm100mm)

Handling instruction:

End-Use Suitability:

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto Spa reserve the rights to change paramethers with no previous notice.We recommend that any fabric has to be carefully evaluated on the basis of final employ.Lenzi Egisto spa can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.