

Fabric Certificate: KOALA STRETCH

Identification		Construction	
Reference name:	KOALA STRETCH	weight:(± 5%)	380 field gr/sqm (ISO 3801)
Usable width cm.:	120 (± 3%)	weight:(± 5%)	455 grs./lin mt. (ISO 3801)
		Comp.:	92%PA 8%EA

Performance				
		Warp	Weft	Test Methods
Tensile Strength-Max force: (Newton)		>3105	>1190	ISO 1421 method 1
Extension at max force: (Percentage)		66%	142%	
Extension at break : (Percentage)		66%	172%	
Abrasion resistance: (nu Martindale)	dry: >51.200 wet:>51.200			UNI EN 13520 (12 kPa)
Pilling: (nu Martindale, after 51.200 revs)	absent			UNI EN 13520 (12kpa)
Repeated flexing test: ("Bally" method)	>250.000			UNI EN 13512

Note:

Please note that above mentioned data are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. cannot be responsible for a fabric used when its technical features are not suitable for its end use.

FF S.r.l.

Registered Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy
 Tel. +39 0574.946030 / 0574.946599 – Fax. +39 0574.946048
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it
 VAT Number: 06270040485