

LENZI EGISTO by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599
- Fax + 39 (0) 574.946048/ 0574.22115
e-mail: lab.resp@lenzie.it – <http://www.lenzie.it>
Codice Fiscale /P.IVA 06270040485

Fabric Certificate: KRAKATOA

Certificate Issued: 24-04-2015

Identification		Construction	
Reference name:	KRAKATOA	weight:(± 5%)	250 field gr/sqm (ISO 3801)
Usable width cm.:	157 (± 2%)	weight:(± 5%)	390 grs./lin mt. (ISO 3801)
		Comp.:	70%preox 30%AR

Weaving			Warp	Weft
Finishing		End count	Yarns:	

Brands:

Performance				
		Warp	Weft	Test Methods
Abrasion resistance: (nu Martindale)				ISO 12947 (9 kPa)
Tear strength: (Newton , singler tear)		>84	>56	EN ISO 13937-2
Pilling: (nu Martindale)				ISO 12947
Tensile Strength (Newton) Extension (Percentage)		>654 10%	>562 12%	BS EN ISO 13934-1(100mm100mm)

Handling instruction:

End-Use Suitability:

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto Spa reserve the rights to change paramethers with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto spa can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.