

# LENZI EGISTO by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599  
 - Fax + 39 (0) 574.946048/ 0574.22115  
 e-mail: [lab.resp@lenzie.it](mailto:lab.resp@lenzie.it) – <http://www.lenzie.it>  
 Codice Fiscale /P.IVA 06270040485

## Fabric Certificate: MONTBLANC



Certificate Issued: 31/10/2013

Identification		Construction	
Reference name:	MONTBLANC	weight:(± 5%)	315 field gr/sqm (ISO 3801)
Usable width cm.:	150 (± 2%)	weight:(± 5%)	472 grs./lin mt. (ISO 3801)
		Comp.:	65%PA 35%PL

Weaving			Warp	Weft
Finishing		End count	Yarns:	

Brands:

### Performance

		Warp	Weft	Test Methods
<b>Abrasion resistance:</b> DRY (nu Martindale)	>100.000			UNI EN 13520 (12 kPa)
WET	>100.000			
<b>Tear strength:</b> (Newton , singler tear)		>340	>295	EN ISO 13937-2
<b>Pilling:</b> (nu Martindale)	4/5			UNI E 15.12.434.0/93
<b>Tensile Strength</b> (Newton)				
<b>Extension</b> (Percentage)		>2185 45%	>2265 38%	BS EN ISO 13934-1(100mm100mm)
<b>Seam Strenght (N/mm)</b>		11.7 39%	11.1 42%	UNI EN 13572

Handling instruction:

End-Use Suitability:

### Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto Spa reserve the rights to change paramethers with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto spa can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.