



LENZI EGISTO®

## Fabric Certificate: NIKA DYNEEMA HEAVY TINTO

Identification		Construction	
Reference name:	NIKA DYNEEMA HEAVY TINTO	weight:(± 5%)	265 field gr/sqm (ISO 3801)
Usable width cm.:	145 (± 2%)	weight:(± 5%)	384 grs./lin mt. (ISO 3801)
		Comp.:	84%PA 16%UHM

Weaving			Warp	Weft
Finishing		End count	Yarns:	

Brands: DYNEEMA®

Performance				
		Warp	Weft	Test Methods
<b>Tear strength:</b> (Newton , singler tear)		>106	>126	UNI EN ISO 13937-2
<b>Tensile Strength:</b> (Newton)		>1370	>2535	UNI EN ISO 13934-1
<b>Extension :</b> (Percentage)		>27%	>36%	
<b>Abrasion resistance:</b> (nu Martindale)	Dry: >100.000 Wet:>100.000			ISO 13520 (12 kPa)
<b>Pilling:</b> (nu Martindale, after 51.200 revs)	absent			ISO 13520 (12kPa)
<b>Repeated flexing resistance:</b> ("Bally" method, n. of flexing)	>150.000			UNI 4818 (Parte/Section 13°)
<b>Seam slippage: (N)</b>		>110	>102	UNI EN 13936-1 (3 mm)

### Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.

#### FF S.r.l.

Registred Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy

Tel. +39 0574.946030/ 0574.946599 - Fax. +39 0574.946048

e-mail: lab.resp@lenziegisto.it - web: www.lenziegisto.it

VAT Number: 06270040485