

# LENZI EGISTO by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599  
 - Fax + 39 (0) 574.946048/ 0574.22115  
 e-mail: [lab.resp@lenzie.it](mailto:lab.resp@lenzie.it) – http: www.lenzie.it  
 Codice Fiscale /P.IVA 06270040485

## Fabric Certificate: NYTECH 1PU WR

### Certificate Issued:

Identification		Construction	
Reference name:	NYTECH 1UP WR	weight:(± 5%)	370 field gr/sqm (ISO 3801)
Usable width cm.:	140 (± 2%)	weight:(± 5%)	518 grs./lin mt. (ISO 3801)
		Comp.:	100% PA

Weaving			Warp	Weft
Finishing		End count	Yarns:	

Brands:

### Performance

		Warp	Weft	Test Methods
<b>Abrasion resistance:</b> (nu Martindale)	dry:> 100.000 wet:> 100.000			ISO 13520 (12 kPa)
<b>Tear strength:</b> (Newton , singler tear)		> 262	>300	EN ISO 13937-2
<b>Pilling:</b> (nu Martindale, after 51.200 revs)	absent			ISO 13520 (12 KpA)
<b>Tensile Strength</b> (Newton) <b>Extension</b> (Percentage)		>2622 55%	>2792 44%	BS EN ISO 13934-1(200mm100mm)
<b>Surface water repellent:</b> (spray test)	4/5			ISO 4920

Handling instruction:

End-Use Suitability:



### Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto Spa reserve the rights to change paramethers with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto spa can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.