

Fabric Certificate: PUTEK 19208 B FF

Identification		Construction	
Reference name:	PUTEK 19208 B FF	weight:(± 5%)	485 field gr/sqm (ISO 3801)
Usable width cm.:	142 (± 2%)	weight:(± 5%)	690 grs./lin mt. (ISO 3801)
		Comp.:	52%PA 43%PU 5%PL

Performance

		Warp	Weft	Test Methods
Tear strength: (Newton , singler tear)		>170	>230	UNI EN 9073-4
Tensile Strength: (Newton) Extension : (Percentage)		>1600 58%	>765 32%	UNI EN ISO 20344 pretension 5N
Seam slippage: (N)		>200	>200	UNI EN 13936-1 (3 mm)
Abrasion resistance: (nu Martindale)	dry: >100.000 wet: >100.000			UNI EN 13520 (12 kPa)
Pilling: (nu Martindale, after 51.200 revs)	absent			UNI EN 13520 (12kpa)
Repeated flexing test: ("Bally" method)	>150.000			UNI EN 13512

Note:

Please note that above mentioned data are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. cannot be responsible for a fabric used when its technical features are not suitable for its end use.

FF S.r.l.

Registred Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy
 Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it
 VAT Number: 06270040485