

# LENZI EGISTO by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599  
- Fax + 39 (0) 574.946048/ 0574.22115  
e-mail: [lab.resp@lenzie.it](mailto:lab.resp@lenzie.it) – <http://www.lenzie.it>  
Codice Fiscale /P.IVA 06270040485

## Fabric Certificate:PUTEK SPIDER WR FF

Identification		Construction	
Reference name:	PUTEK SPIDER WR FF	weight:(± 30)	475 field gr/sqm (ISO 3801)
Usable width cm.:	148 (± 2%)	weight:(± 60)	700 grs./lin mt. (ISO 3801)
		Comp.:	48%PA 47%PU 5%PL

### Performance

		Warp	Weft	Test Methods
<b>Abrasion resistance:</b> (nu Martindale)	dry: >1.000.000 wet: >910.000			UNI 13520 (12 kPa)
<b>Tear strength:</b> (Newton , singler tear)		>127	>128	EN ISO 13937-2
<b>Pilling:</b> (nu Martindale)	4/5			ISO 13520
<b>Tensile Strength</b> (Newton) <b>Extension</b> (Percentage)		>1870 41%	>1730 37%	BS EN ISO 13934-1(200mm100mm)
<b>Seam Strenght</b> (N/mm)		10 48%	9.44 49%	UNI EN 13572
<b>Snagging resistance:</b>	5			ASTM D3939, 600 revs*
<b>Surface wetting resistance:</b> (spray test)	4/5			UNI EN ISO 4920

**Handling instruction:**

**End-Use Suitability:**

**Test executed by Brachi testing services, notified lab n. 0224**

#### Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto by FF laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto by FF reserve the rights to change paramethers with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egistoby FF can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.