

# LENZI EGISTO by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599  
 - Fax + 39 (0) 574.946048/ 0574.22115  
 e-mail: [lab.resp@lenzie.it](mailto:lab.resp@lenzie.it) – <http://www.lenzie.it>  
 Codice Fiscale /P.IVA 06270040485

## Fabric Certificate:PUTEK STRETCH TINTO

2016/05/16

Identification		Construction	
Reference name:	PUTEK STRETCH TINTO	weight:(± 5%)	450 field gr/sqm (ISO 3801)
Usable width cm.:	150 (± 2%)	weight:(± 5%)	675 grs./lin mt. (ISO 3801)
		Comp.:	56%PA 38%PU 6%LY

Weaving			Warp	Weft
Finishing		End count	Yarns:	

Brands:

Performance				
		Warp	Weft	Test Methods
<b>Abrasion resistance:</b> DRY:	>100.000			ISO 13520 (12 kPa)
(nu Martindale) WET:	>100.000			
<b>Tear strength:</b> (Newton , singler tear)		>67	>82	EN ISO 13937-2
<b>Pilling:</b> (nu Martindale)	4/5			ISO 12947
<b>Tensile Strength</b> (Newton)		>1585	>745	BS EN ISO 13934-1(200mm100mm)
<b>Extension</b> (Percentage)		42%	70%	
<b>Snagging resistance:</b>	5			ASTM D3939, 600 revs*

**Handling instruction:**

**End-Use Suitability:**

\*test executed by Brachi testing services, notified lab n. 0224

**Note:**

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto by FF laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto by FF reserve the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto by FF can not be responsible for a fabric used when its technical characteristic are not suitable for its end use.