



# LENZI EGISTO®

## Fabric Certificate: PUTEK WW FF

Identification		Construction	
Reference name:	PUTEK WW FF	weight:(± 25g)	460 field gr/sqm (ISO 3801)
Usable width cm.:	150 (± 2 cm)	weight:(± 50g)	690 grs./lin mt. (ISO 3801)
		Comp.:	55%PA 40%PU 5%PL

Performance				
		Warp	Weft	Test Methods
<b>Abrasion resistance:</b> (nu Martindale)	>100.000			ISO 13520 (12 kPa)
<b>Tear strength:</b> (Newton , singler tear)		>147	>158	EN ISO 13937-2
<b>Pilling:</b> (nu Martindale)	4/5			ISO 13520
<b>Tensile Strength</b> (Newton) <b>Extension</b> (Percentage)		>2377 48%	>4000 32%	BS EN ISO 13934-1(200mm100mm)
<b>Seam Strenght</b> (N/mm)		9.08 47%	6.48 29%	UNI EN 13572

**Handling instruction:**  
**End-Use Suitability:**

### Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto by FF laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto by FF reserve the rights to change paramethers with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto by FF can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.

#### Lenzi Egisto by FF S.r.l.

Registred Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy  
Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048  
e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it  
VAT Number: 06270040485