

Fabric Certificate: SPORTAIR LE 2076

Identification		Construction	
Reference name:	SPORTAIR LE 2076	weight:(± 5%)	260 field gr/sqm (ISO 3801)
Usable width cm.:	144 (± 2%)	weight:(± 5%)	375 grs./lin mt. (ISO 3801)
		Comp.:	100%PA

Performance				
		Warp	Weft	Test Methods
Tear strength: (Newton , singler tear)		>235	>210	UNI EN ISO 4674-1 method b
Tensile Strength: (Newton)		>910	>845	UNI EN ISO 20344 25x75mm samples pretension 10 N
Extension : (Percentage)		51%	49%	
Abrasion resistance: (nu Martindale)	dry: >51.200 wet: >51.200			UNI EN 13520 (12 kPa)
Pilling: (nu Martindale, after 51.200 revs)	absent			UNI EN 13520 (12kpa)
Repeated flexing test: ("Bally" method)	>100.000			UNI EN 13512

Note:

Please note that above mentioned data are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. cannot be responsible for a fabric used when its technical features are not suitable for its end use.

FF S.r.l.

Registred Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy
 Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it
 VAT Number: 06270040485