

Fabric Certificate: ARIA RECYCLED

Identification		Construction	
Reference name:	ARIA RECYCLED	weight:(± 5%)	300 field gr/sqm (ISO 3801)
Usable width cm.:	143 (± 2%)	weight:(± 5%)	430 grs./lin mt. (ISO 3801)
		Comp.:	63%PA 37% RECYCLED PL

Performance

		Warp	Weft	Test Methods
Tear strength: (Newton , singler tear)		>75	>84	UNI EN ISO 13937-2
Tensile Strength: (Newton) Extension : (Percentage)		>1750 42%	>1400 40%	UNI EN ISO 13934-1
Abrasion resistance: (nu Martindale)	dry: >100.000 wet: >100.000			UNI EN 13520 (12 kPa)
Pilling: (nu Martindale, after 51.200 revs)	slight			UNI EN 13520 (12kpa)
Repeated flexing test: ("Bally" method)	>150.000			UNI EN 13512

Note:

Please note that above mentioned data are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. cannot be responsible for a fabric used when its technical features are not suitable for its end use.

FF S.r.l.

Registred Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy
 Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it
 VAT Number: 06270040485