

Fabric Certificate: FLASH LE 17211

Identification		Construction	
Reference name:	FLASH LE 17211	weight:(± 5%)	465 field gr/sqm (ISO 3801)
Usable width cm.:	138 (± 2%)	weight:(± 5%)	640 grs./lin mt. (ISO 3801)
		Comp.:	51%PL TPE 49% PA

Performance				
		Warp	Weft	Test Methods
Tear strength: (Newton , singler tear)		>240	>200	UNI EN ISO 13937-2
Tensile Strength: (Newton)		>1725	>1360	UNI EN ISO 13934-1
Extension : (Percentage)		26%	64%	
Abrasion resistance: (nu Martindale)	Dry: >100.000 Wet: >100.000			UNI EN 13520 (12 kPa)
Pilling: (nu Martindale, after 51.200k revs)	absent			ISO 12947 (12kpa)

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. can not be responsible for a fabric used when its technical characteristics are not suitable for its end use.

FF S.r.l.

Registered Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy
 Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it
 VAT Number: 06270040485