

## Fabric Certificate: FLASH LE 19178 FF

Identification		Construction	
Reference name:	FLASH LE 19178 ff	weight:(± 5%)	510 field gr/sqm (ISO 3801)
Usable width cm.:	135 (± 2%)	weight:(± 5%)	690 grs./lin mt. (ISO 3801)
		Comp.:	52%PL TPE 48% PA

Performance				
		Warp	Weft	Test Methods
<b>Tear strength:</b> (Newton , singler tear)		>195	>415	UNI EN ISO 13937-2
<b>Tensile Strength:</b> (Newton)		>1845	>925	UNI EN ISO 13934-1
<b>Extension :</b> (Percentage)		68%	79%	
<b>Abrasion resistance:</b> (nu Martindale)	Dry: >100.000  Wet: >100.000			UNI EN 13520 (12 kPa)
<b>Pilling:</b> (nu Martindale, after 51.200k revs)	absent			ISO 12947 (12kpa)

### Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.

#### FF S.r.l.

Registred Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy  
 Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048  
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it  
 VAT Number: 06270040485