

Fabric Certificate: LE 19111 RECYCLED REINFORCED

Identification		Construction	
Reference name:	LE 19111 RECYCLED REINFORCED	weight:(± 5%)	380 field gr/sqm (ISO 3801)
Usable width cm.:	142 (± 2%)	weight:(± 5%)	540 grs./lin mt. (ISO 3801)
		Comp.:	52%RECYCLED PL 48%PA

Performance

		Warp	Weft	Test Methods
Tear strength: (Newton , singler tear)		>200	>120	UNI EN ISO 4674-1 method b
Tensile Strength: (Newton) Extension : (Percentage)		>1700 62%	>1140 60%	UNI EN ISO 20344 pretension 5N
Abrasion resistance: (nu Martindale)	dry: >51.200 wet:>51.200			UNI EN 13520 (12 kPa)
Pilling: (nu Martindale, after 12.800 revs)	absent			UNI EN 13520 (12kpa)
Repeated flexing test: ("Bally" method)	>150.000			UNI 4818-13

Note:

Please note that above mentioned data are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. cannot be responsible for a fabric used when its technical features are not suitable for its end use.

FF S.r.l.

Registred Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy
 Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it
 VAT Number: 06270040485