

Fabric Certificate: LE 19116B RECYCLED REINFORCED FF

Identification		Construction	
Reference name:	LE 19116B RECYCLED REINFORCED FF	weight:(± 5%)	330 field gr/sqm (ISO 3801)
Usable width cm.:	143 (± 2%)	weight:(± 5%)	470 grs./lin mt. (ISO 3801)
Repeat cm:	38	Comp.:	51%PA 49%RECYCLED PL

Performance				
		Warp	Weft	Test Methods
Tear strength: (Newton , singler tear)		>177	>147	UNI EN ISO 4674-1 method b
Tensile Strength: (Newton) Extension : (Percentage)		>1650 55%	>1100 66%	UNI EN ISO 20344 pretension 5N
Abrasion resistance: (nu Martindale)	dry: >51.200 wet:>51.200			UNI EN 13520 (12 kPa)
Pilling: (nu Martindale, after 12.800 revs)	absent			UNI EN 13520 (12kpa)
Repeated flexing test: ("Bally" method)	>150.000			UNI 4818-13

Note:

Please note that above mentioned data are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. cannot be responsible for a fabric used when its technical features are not suitable for its end use.

FF S.r.l.

Registred Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy
 Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it
 VAT Number: 06270040485