

Fabric Certificate: PANGU KE

Certificate Issued:

Identification		Construction	
Reference name:	PANGU KE	weight:(± 5%)	335 field gr/sqm (ISO 3801)
Usable width cm.:	140 (± 2%)	weight:(± 5%)	470 grs./lin mt. (ISO 3801)
		Comp.:	93% PA 7% AR

Brands: KEVLAR®, CORDURA®

Performance				Test Methods
		Warp	Weft	
Tear strength: (Newton , singler tear)		>125	>120	UNI EN ISO 13937-2
Tensile Strength: (Newton) Extension : (Percentage)		>2995 47%	>1395 21%	UNI EN ISO 13934-1
Abrasion resistance: (nu Martindale)	DRY>100.000 WET>100.000			ISO 13520 (12 kPa)
Pilling: (nu Martindale)	4/5			ISO 12947

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change paramethers with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.

FF S.r.l.

Registred Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy
 Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it
 VAT Number: 06270040485