

# LENZI EGISTO by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599  
- Fax + 39 (0) 574.946048/ 0574.22115  
e-mail: [lab.resp@lenzie.it](mailto:lab.resp@lenzie.it) – <http://www.lenzie.it>  
Codice Fiscale /P.IVA 06270040485

## Fabric Certificate:PEOX TINTO

Certificate Issued:27-10-2017

Identification		Construction	
Reference name:	PEOX TINTO	weight:(± 5%)	700 field gr/sqm (ISO 3801)
Usable width cm.:	150 (± 2%)	weight:(± 5%)	1050 grs./lin mt. (ISO 3801)
		Comp.:	100%PL

Weaving			Warp	Weft
Finishing		End count	Yarns:	

Brands:

Performance				
		Warp	Weft	Test Methods
<b>Abrasion resistance:</b> (nu Martindale)	>50.000			ISO 12947 (9 kPa)
<b>Tear strength:</b> (Newton , singler tear)		>364	>392	EN ISO 13937-2
<b>Tensile Strength</b> (Newton) <b>Extension</b> (Percentage)		>3000 45%	>3000 34%	BS EN ISO 13934-1(200mm100mm)
<b>Seam Slippage (N)</b> <b>Seam Unseamed</b>		19 >200	15 >200	UNI EN 13936/1 (3 mm)

Handling instruction:

End-Use Suitability:

### Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto by FF laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto by FF reserve the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto by FF can not be responsible for a fabric used when its technical characteristic are not suitable for its end use.