

Fabric Certificate: PPB TRILAMINATO PU WR HT

Certificate Issued:

Identification		Construction	
Reference name:	PPB TRILAMINATO PU WR HT	weight:(± 5%)	320 field gr/sqm (ISO 3801)
Usable width cm.:	160 (± 2%)	weight:(± 5%)	512 grs./lin mt. (ISO 3801)
		Comp.:	100%PL

Weaving	REPS	Warp	Weft
Finishing		End count	Yarns:

Brands:

Performance				
		Warp	Weft	Test Methods
Tear strength: (Newton , singler tear)		≥12	≥12	ASTM D 2261
Tensile Strength (Kgf)		>140	>140	ASTM D 5034
Abrasion resistance: (Taber)	>1800			ASTM D 3884:09 100 GR
Surface water repellance: (spray test)	4/5			ISO 4920
Colour fastness to light:	5			AATCC METHOD 16 xenoarc, blue scale 1:8
Colour fastness to home washing (30°)	Degradation	≥ 4		AATCC METHOD 61-2A GREY SCALE ISO R 105
	Discharge	≥ 4		
Colour fastness to perspiration:		Acid	Alkaline	AATCC TEST 15 grey scale ISO R 105
	Degradation	≥4	≥4	
	Discharge	≥4	≥4	

Handling instruction & end-use suitability:

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. can not be responsible for a fabric used when its technical characteristics are not suitable for its end use.

FF S.r.l.

Registered Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy
 Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it
 VAT Number: 06270040485