



LENZI EGISTO®

Fabric Certificate: PUTEK LE 18111 FF

Identification		Construction	
Reference name:	PUTEK LE18111 FF	weight:(± 5%)	400 field gr/sqm (ISO 3801)
Usable width cm.:	140 (± 2%)	weight:(± 5%)	560 grs./lin mt. (ISO 3801)
		Comp.:	59%PA 36%PU 5%PL

Performance

		Warp	Weft	Test Methods
Tear strength: (Newton , singler tear)		>92	>41	UNI EN ISO 13937-2
Tensile Strength: (Newton) Extension : (Percentage)		>3332 >39%	>635 >28%	UNI EN ISO 13934-1
Abrasion resistance: (nu Martindale)	dry: >100.000 wet: >100.000			UNI EN 13520 (12 kPa)

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. can not be responsible for a fabric used when its technical characteristics are not suitable for its end use.

FF S.r.l.

Registered Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy
Tel. +39 0574.946030 / 0574.946599 – Fax. +39 0574.946048
e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it
VAT Number: 06270040485