

Fabric Certificate: PUTEK LE 18154 BICOLOR FF

Identification		Construction	
Reference name:	PUTEK LE 18154 BICOLOR FF	weight:(± 5%)	535 field gr/sqm (ISO 3801)
Usable width cm.:	147 (± 2%)	weight:(± 5%)	786 grs./lin mt. (ISO 3801)
		Comp.:	52%PU 40%PA 8%PL

Performance				
		Warp	Weft	Test Methods
Tear strength: (Newton , singler tear)		> 200	> 165	UNI EN ISO 13937-2
Tensile Strength: (Newton)		>2309	> 1078	UNI EN ISO 13934-1
Extension : (Percentage)		>33%	>24%	
Abrasion resistance: (nu Martindale)	Dry: >100.000 Wet:>100.000			ISO 13520 (12 kPa)
Pilling: (nu Martindale, after 51.200 revs)	moderate			ISO 13520
Repeated flexing test: ("Bally" method)	>150.000			UNI 4818 (Parte/Section 13°)
Seam Slippage: (Newton)		>103	>123	ISO 13936-1

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. can not be responsible for a fabric used when its technical characteristic are not suitable for its end use.

FF S.r.l.

Registered Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy
 Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it
 VAT Number: 06270040485