

## Fabric Certificate: PUTEK LE 18163 C FF

Identification		Construction	
Reference name:	PUTEK LE 18163 C FF	weight:(± 5%)	570 field gr/sqm (ISO 3801)
Usable width cm.:	146 (± 2%)	weight:(± 5%)	832 grs./lin mt. (ISO 3801)
		Comp.:	47%PU 46%PA 7%PL

Performance				
		Warp	Weft	Test Methods
<b>Tear strength:</b> (Newton , singler tear)		>160	>169	UNI EN ISO 13937-2
<b>Tensile Strength:</b> (Newton) <b>Extension :</b> (Percentage)		>2804 69%	>1158 27%	UNI EN ISO 13934-1
<b>Abrasion resistance:</b> (nu Martindale)	dry:>100.000 wet:>100.000			UNI EN 13520 (12 kPa)
<b>Pilling:</b> (nu Martindale, after 100.000 revs)	absent			UNI EN 13520 (12 kPa)
<b>Repeated flexing test:</b> ( "Bally" method)	>150.000			UNI 4818 (Parte/Section 13°)

### Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. can not be responsible for a fabric used when its technical characteristics are not suitable for its end use.

#### FF S.r.l.

Registered Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy  
 Tel. +39 0574.946030 / 0574.946599 – Fax. +39 0574.946048  
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it  
 VAT Number: 06270040485