

Fabric Certificate: REKE DRILL WR

Identification		Construction	
Reference name:	REKE DRILL WR	weight:(± 5%)	495 field gr/sqm (ISO 3801)
Usable width cm.:	175 (± 2%)	weight:(± 5%)	865 grs./lin mt. (ISO 3801)
		Comp.:	97% AR 3% AF

Performance				
		Warp	Weft	Test Methods
Tear strength: (Newton , singler tear)		>269	>279	UNI EN ISO 13937-2
Tensile Strength: (Newton) Extension : (Percentage)		>2697 16%	>1630 7%	UNI EN ISO 13934-1
Abrasion resistance: (nu Martindale)	>42.000			ISO 12947-2 (12 kPa)
Pilling: (nu Martindale)	4/5			ISO 12947-2 (12 kPa)
Surface water repellance (spray test)	≥4			ISO 4920

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change paramethers with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.

FF S.r.l.

Registred Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy
 Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it
 VAT Number: 06270040485