

LENZI EGISTO by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599
- Fax + 39 (0) 574.946048/ 0574.22115
e-mail: lab.resp@lenzie.it – <http://www.lenzie.it>
Codice Fiscale /P.IVA 06270040485

Fabric Certificate: STEALTH WR

Identification		Construction	
Reference name:	STEALTH WR	weight:(± 10%)	230 field gr/sqm (ISO 3801)
Usable width cm.:	151 (± 3 cm)	weight:(± 10%)	345 grs./lin mt. (ISO 3801)
		Comp.:	100%PL

Performance

		Warp	Weft	Test Methods
Abrasion resistance: (nu Martindale)	40.000			ISO 12947 (9 kPa)
Abrasion resistance: (nu Martindale, method for footwear and lining)	Dry:>38.400 Wet:>25.600			EN ISO 13520 (12 Kpa)
Tear strength: (daNewton , singler tear)		>30	>35	EN ISO 13937-2
Pilling: (nu Martindale)	4/5			ISO 12947
Tensile Strength (daNewton) Extension (Percentage)		>350 32%	>300 68%	BS EN ISO 13934-1(200mm100mm)
Colour fastness to light	5			ISO 105 B-02
Colour fastness to water	4/5			ISO 105 E-01
Colour fastness to Dry rubbing	4			ISO 105 X-12
Colour fastness to Wet rubbing	4			
Colour fastness to perspiration		ACID 4/5	ALCALINE 4/5	ISO 105 E-04

Handling instruction:

End-Use Suitability:

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto Spa reserve the rights to change paramethers with no previous notice.We recommend that any fabric has to be carefully evaluated on the basis of final employ.Lenzi Egisto spa can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.