

# LENZI EGISTO by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599  
 - Fax + 39 (0) 574.946048/ 0574.22115  
 e-mail: [lab.resp@lenzie.it](mailto:lab.resp@lenzie.it) – <http://www.lenzie.it>  
 Codice Fiscale /P.IVA 06270040485

Certificate Issued: 03/04/2012

Identification		Construction	
Reference name:	STROMBOLI	Weight(±5%):	398 field gr/sqm (ISO 3801)
Usable width cm.:	150 +/-2%	Weight(±5%):	597 grs./lin mt. (ISO 3801)
		Comp.:	70%PAN 30%AR

Weaving			Warp	Weft
Finishing			End count	Yarns:

Brands: KEVLAR®

## Performance

		Warp	Weft	Test Methods
<b>Abrasion resistance:</b> (nu Martindale)	10.000			ISO 12947 (9 kPa)
<b>Tear strength:</b> (Newton , singler tear)		>32	>29	EN ISO 13937-2
<b>Pilling:</b> (nu Martindale)	4/5			ISO 12947
<b>Tensile Strength</b> (Newton) <b>Extension</b> (Percentage)		>850 9%	>990 13%	BS EN ISO 13934-1
<b>Seam slippage : (N) Seam:</b> <b>Unseamed:</b>		171 >200	145 >200	UNI EN ISO 13936 (3 mm)

Handling instruction:

End-Use Suitability:

### Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto Spa reserve the rights to change paramethers with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto spa can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.