

LENZI EGISTO by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599
 - Fax + 39 (0) 574.946048/ 0574.22115
 e-mail: lab.resp@lenzie.it – http: www.lenzie.it
 Codice Fiscale /P.IVA 06270040485

Fabric Certificate:STUOIA NYCO DELAVE' FF

Certificate Issued: 07/07/2014

Identification		Construction	
Reference name:	STUOIA NYCO DELAVE' FF	weight:(± 5%)	493 field gr/sqm (ISO 3801)
Usable width cm.:	140 (± 2%)	weight:(± 5%)	690 grs./lin mt. (ISO 3801)
		Comp.:	75%PA 25%CO

Weaving			Warp	Weft
Finishing		End count	Yarns:	

Brands:

Performance				
		Warp	Weft	Test Methods
Abrasion resistance: (nu Martindale)	DRY: >51.200 WET: >51.200			ISO 13520 (12 kPa)
Tear strength: (Newton , singler tear)		>138	>71	EN ISO 13937-2
Pilling: (nu Martindale)	4			ISO 13520
Tensile Strength (Newton) Extension (Percentage)		>1655 37%	>2790 27%	BS EN ISO 13934-1(100mm100mm)

Handling instruction:

End-Use Suitability:

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto by FF laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto by FF reserve the rights to change paramethers with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto by FF can not be responsible for a fabric used when its thecnical characteristic are not suitable for its end use.