


LENZI EGISTO by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599
 - Fax + 39 (0) 574.946048/ 0574.22115
 e-mail: lab.resp@lenzie.it – <http://www.lenzie.it>
 Codice Fiscale /P.IVA 06270040485

Fabric Certificate:SUMO WR

Identification		Construction	
Reference name:	SUMO WR	weight:(± 5%)	265 field gr/sqm (ISO 3801)
Usable width cm.:	153 (± 3 cm)	weight:(± 5%)	405 grs./lin mt. (ISO 3801)
		Comp.:	90%PA 10%EA

Weaving			Warp	Weft
Finishing		End count	Yarns:	

Brands: LYCRA®,CORDURA®

Performance				
		Warp	Weft	Test Methods
Abrasion resistance: (nu Martindale)	>100.000			ISO 12947 (9 kPa)
Tear strength: (Newton , singler tear)		>55	>30	EN ISO 13937-2
Pilling: (nu Martindale)	4/5			ISO 12947
Tensile Strength (Newton) Extension (Percentage)		>1190 135%	>770 65%	BS EN ISO 13934-1(100mm100mm)
Seam slippage: (N) Seam:		>200	>200	UNI EN 13936-1 (3 mm)
Unseamed:		>200	>200	
Surface water repellance: (spray test)	4/5			ISO 4920

Handling instruction:
End-Use Suitability:

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto by FF laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto by FF reserve the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto by FF can not be responsible for a fabric used when its technical characteristic are not suitable for its end use.