

Fabric Certificate: SUMONOS HEXAGON 11

Identification		Construction	
Reference name:	SUMONOS HEXAGON 11	weight:(± 5%)	465 field gr/sqm (ISO 3801)
Usable width cm.:	135 (± 2%)	weight:(± 5%)	628 grs./lin mt. (ISO 3801)
Stacco Piastra-Plate interval:	95 cm	Comp.:	54%PA 37%PL 9%LY

Performance			
	Warp	Weft	Test Methods
Tear strength: (Newton , singler tear)	>44	>32	UNI EN ISO 13937-2
Tensile Strength (Newton)	>1060	>615	UNI EN ISO 13934-1
Extension (Percentage)	57%	97%	
Abrasion resistance: (nu Martindale)	>13.000		ISO 12947 (9 kPa)
Pilling: (nu Martindale)	4		ISO 12947
Appearance change: (nu Martindale, after 20k rubs)	No change		ISO 12947-4

Handling instruction & end-use suitability:



Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. can not be responsible for a fabric used when its technical characteristics are not suitable for its end use.

FF S.r.l.

Registered Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy
 Tel. +39 0574.946030 / 0574.946599 – Fax. +39 0574.946048
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it
 VAT Number: 06270040485