

Fabric Certificate: SUMONOS HEXAGON 5

| Identification | | Construction | |
|--------------------------------|-------------------|---------------|-----------------------------|
| Reference name: | SUMONOS HEXAGON 5 | weight:(± 5%) | 465 field gr/sqm (ISO 3801) |
| Usable width cm.: | 135 (± 2%) | weight:(± 5%) | 628 grs./lin mt. (ISO 3801) |
| Stacco Piastra-Plate interval: | 95 cm | Comp.: | 50%PL 42%LY 8%PA |

| Performance | | | | |
|--|-----------|-------|------|--------------------|
| | | Warp | Weft | Test Methods |
| Tear strength: (Newton , singler tear) | | >44 | >32 | UNI EN ISO 13937-2 |
| Tensile Strength (Newton) | | >1060 | >615 | UNI EN ISO 13934-1 |
| Extension (Percentage) | | 57% | 97% | |
| Abrasion resistance: (nu Martindale) | >13.000 | | | ISO 12947 (9 kPa) |
| Pilling: (nu Martindale) | 4 | | | ISO 12947 |
| Appearance change: (nu Martindale, after 20k rubs) | No Change | | | ISO 12947-4 |

Handling instruction & end-use suitability:



Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. can not be responsible for a fabric used when its technical characteristics are not suitable for its end use.

FF S.r.l.

Registered Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy
 Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it
 VAT Number: 06270040485