

LENZI EGISTO by FF

Sede Legale ed amministrativa: Via G. Di Vittorio,52 – I – 59021 VAIANO Tel. +39 (0) 574.946030/ 0574.946599
- Fax + 39 (0) 574.946048/ 0574.22115
e-mail: lab.resp@lenzie.it – <http://www.lenzie.it>
Codice Fiscale /P.IVA 06270040485

Fabric Certificate: TRIAL PES

Certificate Issued:

Identification		Construction	
Reference name:	TRIAL PES	weight:(± 5%)	272 field gr/sqm (ISO 3801)
Usable width cm.:	139 (± 2%)	weight:(± 5%)	378 grs./lin mt. (ISO 3801)
		Comp.:	90% PL 10% LYCRA

Performance

		Warp	Weft	Test Methods
Abrasion resistance: (nu Martindale)	>100.000			(9 Kpa) ISO 12947
Tear strength: (Newton , singler tear)		> 50	> 50	EN ISO 13937-2
Pilling: (nu Martindale)	4/5			ISO 12947
Tensile Strength (Newton) Extension (Percentage)		>1426 114%	>715 60%	BS EN ISO 13934-1(100mm100mm)

Handling instruction:

End-Use Suitability:

Note:

Please note that above mentioned datas are average figures. Results have been obtained by testing at Lenzi Egisto by FF laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. Lenzi Egisto by FF reserve the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. Lenzi Egisto by FF can not be responsible for a fabric used when its technical characteristics are not suitable for its end use.