

Fabric Certificate: VENTO RECYCLED

| Identification | | Construction | |
|-------------------|-----------------------|---------------|------------------------------------|
| Reference name: | VENTO RECYCLED | weight:(± 5%) | 285 field gr/sqm (ISO 3801) |
| Usable width cm.: | 143 (± 2%) | weight:(± 5%) | 410 grs./lin mt. (ISO 3801) |
| | | Comp.: | 66%PA 34% RECYCLED PL |

| Performance | | | | |
|--|--|-------------------------------|-------------------------------|-----------------------|
| | | Warp | Weft | Test Methods |
| Tear strength: (Newton , singler tear) | | >55 | >60 | UNI EN ISO 13937-2 |
| Tensile Strength: (Newton) Extension : (Percentage) | | >1510 43% | >1395 48% | UNI EN ISO 13934-1 |
| Abrasion resistance: (nu Martindale) | dry: >100.000 wet: >100.000 | | | UNI EN 13520 (12 kPa) |
| Pilling: (nu Martindale, after 51.200 revs) | moderate | | | UNI EN 13520 (12kpa) |
| Repeated flexing test: ("Bally" method) | >150.000 | | | UNI EN 13512 |

Note:

Please note that above mentioned data are average figures. Results have been obtained by testing at FF S.r.l. laboratories in Vaiano, following tests and methods procedures as ISO, UNI etc, as stated. FF S.r.l. reserves the rights to change parameters with no previous notice. We recommend that any fabric has to be carefully evaluated on the basis of final employ. FF S.r.l. cannot be responsible for a fabric used when its technical features are not suitable for its end use.

FF S.r.l.

Registred Office: Via G. Di Vittorio, n. 39 - 59021 Vaiano (PO) Italy
 Tel. +39 0574.946030/ 0574.946599 – Fax. +39 0574.946048
 e-mail: lab.resp@lenziegisto.it – web: www.lenziegisto.it
 VAT Number: 06270040485